

AGM LINE SEALED DEEP CYCLE BATTERIES

S12-240AGM

12 VOLTS




HOUR RATE:	SPECIFIC GRAVITY	CAPACITY / AMP HOUR	CURRENT / AMPS
@ 100 HOUR RATE	1.280	240	2.40
@ 20 HOUR RATE	1.280	215	10.75
@ 10 HOUR RATE	1.280	184	18.40
@ 8 HOUR RATE	1.280	180	22.50
@ 5 HOUR RATE	1.280	164	32.80

AT 77°F / 25°C

CAPACITY AFFECTED BY TEMPERATURE (20 HR RATE)				
104°F / 40°C	102%			
77°F / 25°C	100%			
32°F /0°C	85%			
5ºF / -15ºC	65%			


SELF-DISCHARGE 77°F / 25°C		
CAPACITY AFTER 3 MONTHS	91%	
CAPACITY AFTER 6 MONTHS	82%	
CAPACITY AFTER 12 MONTHS	64%	



Certified System	\$ X X X X X X X X X X X X X X X X X X X
sale ISO 90 Quality	01

RESERVE CAPACITY (RC @ 25A):		420
RECOMMENDED CHARGE CURRENT:		43 A
MAX CHARGE CURRENT:		75.2 A
MAXIMUM DISCHARGE CURRENT:		2000 A
CHARGING constant	CYCLE:	14.5-14.9V/cell 77°F / 25°C
voltage	FLOAT:	13.6-13.8V/cell 77°F / 25°C

CYCLE LIFE VS. DEPTH OF DISCHARGE



SURRETTE BATTERY COMPANY 1 STATION RD SPRINGHILL, NS CANADA BOM 1X0